

Allure **SPECIFICATION**

Material

Porcelain stoneware. Classified in GROUP Bla UGL con $E_V \leq 0.5\%$. Complies with all the requirements of UNI EN 14411 ISO 13006 APP. G standards.



	COLOR	SIZES & SURFACES	THICKNESS		
	Rovere Blanc V3				
	Rovere Amande V3	<u>Matte Rectified (9 mm)</u> 20x120 (8"x47 ^{1/4} ") <u>Antislip Rectified (9 mm)</u> 20x120 (8"x47 ^{1/4} ") <u>Open Antislip Rectified (20 mm)</u> 30x120 (11 ^{7/8} "x47 ^{1/4} ")			
1	Rovere Naturel V3		9 mm 20 mm		
	Olmo Ambré V3				
	Olmo Fumé V3				
	Noce Brun V3				

Process certified according to the ISO 9001 quality standard

Product obtained from exceptionally pure, choice quality raw materials, including light-coloured clays, feldspar fluxes, kaolins, sands and coloured ceramic pigments. Pressing in hydraulic presses allows a pressure of over 500kg/cm2 to be applied to the product, guaranteeing dimensional precision, planarity and high mechanical strength. The product's colours and patterns are achieved with the innovative Digital Technology. The materials are fired in single-layer roller kilns at temperatures of over 1,220°C.

Green building certified environmental sustainability

The tiles in the Allure collection are ideal for eco-sustainable building:

放射性水平A拳

EN 14411

LEED

- They are produced in plants which have an EMAS-ISO 14001 certified environmental management system.
- They help to obtain credits for the construction of buildings in accordance with the LEED certification programme.

EPD	()))	CF	"	**** * EMAS	ISO 14001 BUILEAN VERTRAS	SO 6501 BIREAU VISITAS Carricates	SD 9001 Bill A JU VTREAS Certificatos	SILVER 2020 ecoyaciis Sustanabiliy	Certificazione
<u>Color</u>			 <u>Туре</u>						
<u>Finishes</u>	 		 						
<u>Size</u>			 						



ITALGRANITI SUPERIOR ITALIAN SURFACES

<u>Allure</u> **SPECIFICATION**

















FACING SYSTEMS

RESIDENTIAL INDOOR

RESIDENTIAL OUTDOOR















CONFORMING TO STANDARDS

EN 14411 ISO 13006 ANNEX G GROUP BIa UGL CON Ev $\leq 0,5\%$

WALL

	PHYSICAL PROPERTIES TESTING METHOD		REFERENCE STANDARD	PRODUCT VALUES		
				7cm ≤ N < 15 cm (mm)	N ≥ 15 cm (%) (mm)	Rectified
			Length and width	±0.9	±0.6 ±2.0	±0.2 %
		EN ISO 10545-2	Thickness	±0.5	±5.0 ±0.5	±5 %
	Sizes		Linearity	±0.75	±0.5 ±1.5	±0.2 %
			Wedging	±0.75	±0.5 ±2.0	±0.2 %
			Warpage	±0.75	±0.5 ±2.0	±0.2 %
			Appearance: percentage of acceptable tiles, per lot	95 % min.	95 % - min.	
٥	Water absorption %	EN ISO 10545-3	$E_V \le 0.5\%$			< 0,1%
	Modulus of rupture		Valore medio 35 N/mm² min.			45 N/mm²
Ū	Breakage resistence	EN ISO 10545-4	sp. > = 7,5 mm: min 1300 N sp. < 7,5 mm: min 700 N			2300 N (9 mm) 12500 N (20 mm)
0	Scratch resistance	EN ISO 10545-6	175 mm3 max.			Average < 150 mm3
	Thermal expansion coefficient	EN ISO 10545-8	Declared value			6,8 MK ⁻¹
	Thermal shock resistance	EN ISO 10545-9	Pass according to iso 10545-1			* Resistant
*	Frost resistance	EN ISO 10545-12	Pass according to iso 10545-1			* Resistant
	Resistance to low concentrations of acids and alkali		Declared value			* Resistant
R	Resistance to high concentrations of acids and alkali	EN ISO 10545-13	Declared value			* Resistant
	Resistance to domestic chemicals and additives for swimming pools		UB min.			UA
*	Stain resistance of unglazed matte porcelain	EN ISO 10545-14	Declared value			* Resistant
			Annex A			Declared value
		EN 16165	Annex B			Declared value
9	Friction coefficient (slipperiness)	B.C.R.A D.M.236/ 89	If needed	> 0,40 Dry / > 0,40 Wet		
		ANSI A326.3	If needed			≥ 0,42 Wet

