

Nuances

SPECIFICATION

Material

Porcelain stoneware. Classified in GROUP BIa UGL con $E_v \leq 0,5\%$.
 Complies with all the requirements of UNI EN 14411 ISO 13006 APP. G standards.



[Download
Catalog](#)

	COLOR		SIZES & SURFACES	THICKNESS
	Bianco	V2	<u>Mega Naturale Rettificato (6 mm)</u> 120x280 (47^{1/4}"x110^{1/4}") <u>STRIDE UP Naturale Rettificato (9 mm)</u> 120x120 (47^{1/4}"x47^{1/4}") . 60x120 (23^{1/2}"x47^{1/4}") . 80x80 (31^{1/2}"x31^{1/2}") . 40x80 (15^{3/4}"x31^{1/2}") . 60x60 (23^{1/2}"x23^{1/2}") . 30x60 (11^{7/8}"x23^{1/2}") <u>Ribbed Rettificato (9 mm)</u> 60x120 (23^{1/2}"x47^{1/4}") <u>Antislip Rettificato (9 mm)</u> 60x120 (23^{1/2}"x47^{1/4}") <u>Open Antislip Rettificato (20 mm)</u> 60x120 (23^{1/2}"x47^{1/4}")	6 mm 9 mm 20 mm
	Grigio	V2		
	Antracite	V2		
	Nero	V2		
	Avorio	V2		
	Tortora	V2		
	Cipria	V2		
	Marrone	V2		
	Salvia	V2		
	Cielo	V2		
	Fiamma	V2		
	Luce	V2		
	Rose	V2		
	Giada	V2		

Process certified according to the ISO 9001 quality standard

Product obtained from exceptionally pure, choice quality raw materials, including light-coloured clays, feldspar fluxes, kaolins, sands and coloured ceramic pigments. Pressing in hydraulic presses allows a pressure of over 500kg/cm² to be applied to the product, guaranteeing dimensional precision, planarity and high mechanical strength. The product's colours and patterns are achieved with the innovative Digital Technology. The materials are fired in single-layer roller kilns at temperatures of over 1,220°C.

Green building certified environmental sustainability

The tiles in the Nuances collection are ideal for eco-sustainable building:

- They are produced in plants which have an EMAS-ISO 14001 certified environmental management system.
- They help to obtain credits for the construction of buildings in accordance with the LEED certification programme.

Size _____

Finishes _____

Color _____ Type _____



放射性水平A类



EN 14411



Nuances

SPECIFICATION



FLOOR



WALL



FACING SYSTEMS



RESIDENTIAL INDOOR



RESIDENTIAL OUTDOOR



PUBLIC INDOOR



PUBLIC OUTDOOR



HEAVY TRAFFIC

TECHNICAL TABLE PORCELAIN STONEWARE

CONFORMING TO STANDARDS

EN 14411 ISO 13006 ANNEX G GROUP B1a UGL CON Ev ≤ 0,5%

PHYSICAL PROPERTIES	TESTING METHOD	REFERENCE STANDARD	PRODUCT VALUES
 Sizes	EN ISO 10545-2		7 cm ≤ N < 15 cm (mm) N ≥ 15 cm (%) (mm) Rectified
		Length and width	±0.9 ±0.6 ±2.0 ±0.2 %
		Thickness	±0.5 ±5.0 ±0.5 ±5 %
		Linearity	±0.75 ±0.5 ±1.5 ±0.2 %
		Wedging	±0.75 ±0.5 ±2.0 ±0.2 %
		Warpage	±0.75 ±0.5 ±2.0 ±0.2 %
		Appearance: percentage of acceptable tiles, per lot	95 % min. 95 % min. -
 Water absorption %	EN ISO 10545-3	Ev ≤ 0,5%	< 0,1%
 Modulus of rupture	EN ISO 10545-4	Valore medio 35 N/mm ² min.	45 N/mm ²
 Breakage resistance		sp. > = 7,5 mm: min 1300 N sp. < 7,5 mm: min 700 N	2300 N (9 mm) 12500 N (20 mm)
 Scratch resistance	EN ISO 10545-6	175 mm3 max.	Average < 150 mm3
 Thermal expansion coefficient	EN ISO 10545-8	Declared value	6,8 MK ⁻¹
 Thermal shock resistance	EN ISO 10545-9	Pass according to iso 10545-1	* Resistant
 Frost resistance	EN ISO 10545-12	Pass according to iso 10545-1	* Resistant
 Resistance to low concentrations of acids and alkali	EN ISO 10545-13	Declared value	* Resistant
 Resistance to high concentrations of acids and alkali		Declared value	* Resistant
Resistance to domestic chemicals and additives for swimming pools		UB min.	UA
 Stain resistance of unglazed matte porcelain	EN ISO 10545-14	Declared value	* Resistant
 Friction coefficient (slipperiness)	EN 16165	Annex A	Declared value
		Annex B	Declared value
	B.C.R.A. - D.M.236/ 89	If needed	> 0,40 Dry / > 0,40 Wet
	ANSI A326.3	If needed	≥ 0,42 Wet




 Assessed by Ongreening
 This product contributes to major green rating systems.
 For more info visit Ongreening.com



Technical details available on:
www.italgranitigroup.com